



Product Data

Castrol Brayco Micronic 756

Hydraulic fluid, Petroleum base
Aircraft, Missile and Ordnance

Description

Castrol Brayco® Micronic 756 is a petroleum base, low viscosity, red colored ISO Grade 15 hydraulic fluid for aircraft, missile and ordnance use. It is a blend of highly refined, selected base stocks with suitable additives, which yield a product with exceptionally good viscosity-temperature characteristics, good anti-wear properties, low rubber swell, and excellent oxidation stability. The use of a polymeric viscosity index improver of low molecular weight provides stability in comparison to typical hydraulic fluids.

Temperature Range

-54°C to 135°C

Uses

Brayco Micronic 756 is designed for use in aircraft, missile, and ordnance hydraulic systems where long term stability and a low temperature fluid is required. Brayco Micronic 756 is filtered to meet rigid particle contaminant requirements. It is intended for use in automatic pilots, shock absorbers, brakes, flap-control mechanisms, missile hydraulic servo-controlled systems and other hydraulic systems using synthetic sealing materials. Fluids compounded to meet this specification undergo certain changes with use. Further information relative to usable life may be found in Fainman and Mackenzie, "The Characteristics and Performance of Specification MIL-H-5606 Hydraulic Fluid," Lubrication Engineering 22234 (1966).

Packaging

Brayco Micronic 756 is available in 55 gallon drums, 5 gallon pails, 6/1 gallon cases and 24/1 quart cases.

Specification

Brayco Micronic 756 meets the requirements and is qualified under military specification MIL-PRF-5606H. This fluid is identified by Military Symbol: OHA and NATO Code Number: H-515.

Brayco Micronic 756
104460_2006_11
Castrol and the Castrol logo are trademarks of Castrol Limited, used under licence.

All reasonable care has been taken to ensure that the information contained in this publication is accurate as of the date of printing. However, such information may, nevertheless, be affected by changes in the blend formulation occurring subsequent to the date of printing. Material Safety Data Sheets are available for all Castrol products. The MSDS must be consulted for appropriate information regarding storage, safe handling and disposal of a product. See www.msds.castrol.com.au

Castrol Australia Pty Limited, Industrial Lubricants and Services, GPO Box 5222, Melbourne VIC 3001
Technical Advice Line 1300 557 998 / Customer Service 1300 722 088
www.castrol.com/industrial

Typical Characteristics

BRAYCO MICRONIC 756			
TEST METHOD	DESCRIPTION	MIL-H-5606G REQUIREMENTS	RESULT
D 287	API Gravity, degrees	30.5 Typical	30.1
Table 3	Specific Gravity @ 15°C/60°F	0.8735 Typical	0.87
Table 8	Pounds per Gallon @ 15°C/60°F	7.273 Typical	7.28
D 445	Kinematic Viscosity, cSt @ 100°C @ 40°C @ -40°C @ -54°C	4.90 Minimum 13.2 Minimum 600 Maximum 2500 Maximum	5.1 13.5 487 2275
D 97	Pour Point, °C	-60 Maximum	-60
D 93	Flash Point, PMCC, °C	82 Minimum	96
D 664	Acid or Base Number, mgKOH/g	0.20 Maximum	0.03
Spec	Color	Red per standard	Pass
FTM 5308	Corrosion & Oxidation Stability 168 hrs @ 135°C Weight change, mg/cm2 Copper Aluminum Alloy Magnesium Alloy Steel Cadmium Plated Steel Appearance Copper color, ASTM Pitting, etching, corrosion Viscosity change @ 40°C, % Neutralization number increase	 ±0.6 ±0.2 ±0.2 ±0.2 ±0.2 3 Maximum None -5 to +20 0.20 Maximum	 -0.053 -0.023 -0.015 0.000 +0.007 Pass Pass +9.6 0.02
FTM 3459	Low-Temperature Stability -54°C for 72 hrs	No solids or separation	Pass
Spec	Shear Stability, % Viscosity Decrease @ 40°C @ -40°C Change in Acid or Base Number	 15 Maximum 15 Maximum 0.20 Maximum	 0.9 1.23 0.00
FTM 3603	Synthetic Rubber Swell, "L" % Volume Increase of L-Rubber (Buna N)	19.2 to 30.0	28
D 972	Evaporation, 6 hrs @ 71°C	20 Maximum	9.6
D 130	Copper Strip Corrosion, 3 sets, 72 hrs @ 135°C	2e Maximum	2b
FTM 3009	Solid Particle Contamination Number of particles per 100 mL of fluid, auto count 5 - 15 microns 16 - 25 microns 26 - 50 microns 51 - 100 microns 100 & larger	 10,000 1,000 150 20 5	 4500 195 50 10 1

Brayco Micronic 756

104460_2006_11

Castrol and the Castrol logo are trademarks of Castrol Limited, used under licence.

All reasonable care has been taken to ensure that the information contained in this publication is accurate as of the date of printing. However, such information may, nevertheless, be affected by changes in the blend formulation occurring subsequent to the date of printing. Material Safety Data Sheets are available for all Castrol products. The MSDS must be consulted for appropriate information regarding storage, safe handling and disposal of a product. See www.msds.castrol.com.au

Castrol Australia Pty Limited, Industrial Lubricants and Services, GPO Box 5222, Melbourne VIC 3001

Technical Advice Line 1300 557 998 / Customer Service 1300 722 088

www.castrol.com/industrial

Typical Characteristics contd...

TEST METHOD	DESCRIPTION	MIL-H-5606G REQUIREMENTS	RESULT
	Gravimetric Residue mg per 100 mL	0.3 Maximum	0.2
	Filtering Time, minutes	15 Maximum	8.0
D 2270	Viscosity Index		367
D 892 (alt)	Foaming Characteristics @ 24°C Foaming Tendency, mL Foaming stability @ end of 10 minutes	65 Maximum 0 Maximum	35 0
D 1744	Water by KFR, ppm	100 Maximum	36
D 4172	Steel-on-Steel Wear Condition B, AWSD, mm	1 Maximum	0.77
Spec	Workmanship	Pass	Pass
MIL-STD-1844	Chlorine, ppm	50 Maximum	10
	Coefficient of Expansion 15.5°C - 71.1°C per °F		0.00042

SPECIFIC HEAT		THERMAL CONDUCTIVITY	
Temp., °F (°C)	BTU/LB/°F	Temp., °F (°C)	BTU-ft ² /hr/°F
-60 (-54)	0.361	-65 (-54)	0.0816
-30 (-34.4)	0.377	0 (-17.8)	0.0802
0 (-17.8)	0.392	100 (37.8)	0.0777
80 (26.7)	0.453	200 (93.3)	0.0753
150 (65.6)	0.493	300 (148.9)	0.0730
200 (93.3)	0.523		
250 (121.1)	0.552		

BULK MODULUS, ADIABATIC, @ 24°C (76°F)		VAPOR PRESSURE	
Pressure, PSI	Bulk Modulus, PSI	Temp. °C	mm of Hg
0	232,000	145.6	30.3
100	243,000	133.3	17.9
2000	255,000	123.3	12.2
3000	266,000	110.0	6.7
		90.0	2.9
		12.8	0.01
		-17.8	0.0006
		-54.0	0.000005

Additional Information

Brayco Micronic 756 is classified as non hazardous according to the criteria of NOHSC. However, in line with safe handling practices, it is recommended that the handling instructions outlined in the Castrol Material Safety Data Sheet be followed.

Brayco Micronic 756
104460_2006_11
Castrol and the Castrol logo are trademarks of Castrol Limited, used under licence.

All reasonable care has been taken to ensure that the information contained in this publication is accurate as of the date of printing. However, such information may, nevertheless, be affected by changes in the blend formulation occurring subsequent to the date of printing. Material Safety Data Sheets are available for all Castrol products. The MSDS must be consulted for appropriate information regarding storage, safe handling and disposal of a product. See www.msds.castrol.com.au

Castrol Australia Pty Limited, Industrial Lubricants and Services, GPO Box 5222, Melbourne VIC 3001
Technical Advice Line 1300 557 998 / Customer Service 1300 722 088
www.castrol.com/industrial

Brayco Micronic 756 is classified as a C1 combustible liquid for storage and handling purposes. Store in a cool, dry, well-ventilated area out of direct sunlight. Avoid sparks, flames and other ignition sources. Store away from incompatible materials such as materials that support combustion (oxidising materials). Reference should be made to Australian Standard AS1940 - The storage and handling of flammable and combustible liquids.

Spillage:	SMALL - 20 LITRES OR LESS Soak up on Castrol Diatomaceous Earth or similar inert oil absorbent. Arrange for disposal through an approved facility. LARGE - GREATER THAN 20 LITRES Contain as soon as possible, remove by best means available and arrange recycling (preferred) or disposal through an approved facility.
Disposal:	New or used material must not be allowed to enter the ground, ground water, water courses, sewers or drainage systems. Advice may be sought from the Environmental Protection Authority or from the local waste disposal authority.

Brayco Micronic 756
104460_2006_11
Castrol and the Castrol logo are trademarks of Castrol Limited, used under licence.

All reasonable care has been taken to ensure that the information contained in this publication is accurate as of the date of printing. However, such information may, nevertheless, be affected by changes in the blend formulation occurring subsequent to the date of printing. Material Safety Data Sheets are available for all Castrol products. The MSDS must be consulted for appropriate information regarding storage, safe handling and disposal of a product. See www.msds.castrol.com.au

Castrol Australia Pty Limited, Industrial Lubricants and Services, GPO Box 5222, Melbourne VIC 3001
Technical Advice Line 1300 557 998 / Customer Service 1300 722 088
www.castrol.com/industrial