

TECHNICAL DATA

PR-2050 Class B Rapid Curing Aerodynamic Smoothing Compound

Description

PR-2050 Class B is a rapid curing compound designed for aerodynamic smoothing and gap filling applications. It has a service temperature range of -65°F (-54°C) to 250°F (121°C), with intermittent exposures up to 400°F (204°C). This product has low shrinkage and cures to a sandable hardness in at least one hour at 77°F (25°C) or above. When cured, PR-2050 Class B remains flexible, reducing potential cracking problems that can be experienced with more brittle sealing compounds.

PR-2050 Class B is a two-part, epoxy cured, Permapol® P-3.1 polythioether compound. The cured product will not degrade after limited exposure to jet fuel and aviation gas, nor with limited contact to diphosphate ester based hydraulic fluids. PR-2050 Class B exhibits excellent adhesion to a wide variety of properly prepared aircraft surfaces.

The following tests are in accordance with PRC-DeSoto Standard.

Application Properties (Typical)

Color			
Part A	Black		
Part B	White		
Mixed	Dark Gray		
Mixing ratio	Part A:Part B		
By weight	24:100		
By Volume	25:100		
Viscosity			
(Brookfield #7 @ 2 rpm), Poise (Pa-s)			
Part B	17,200(1,720)		
Cure to 55 durometer A	24 hours		
	Application	Tack-Free	Cure to 35
	Life	Time	Durometer A
B-1/4	15 min.	45 min.	1hour
B-1/2	30 min	2 hours	3 hours
B-1	60 min	5 hours	6 hours

Performance Properties (Typical)

Cured 7 days @ 77°F (25°C), 50% RH	
Cured specific gravity	1.5
Nonvolatile content, %	97
Ultimate cure hardness,	
Durometer A	70
Lap shear strength, psi (kN/m2)	
Dry, AMS-C-5516 (Stainless steel)	380 (2620)
Dry, AMS-C-4901 (Titanium)	350 (2413)
Dry, Mil-PRF-85582 (waterborne primer)	400 (2750)
Tensile strength, psi (kPa)	480 (3310)
Tear Strength, lbs/in	40
Elongation, %	80
Sandability	Excellent
Resistance to other fluids - Excellent resistance to water, alcohols, petroleum-base and synthetic lubricating oils, and petroleum-base hydraulic fluids.	

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Surface Preparation

Immediately before applying compound to metallic, chemically treated, epoxy primed, or urethane primed substrates, the surfaces should be cleaned with solvents to remove contamination such as dirt, grease, and/or processing lubricants.

A progressive cleaning procedure should be employed using appropriate solvents and a new lint-free cloth conforming to AMS 3819. (Reclaimed solvents or tissue paper should not be used.) Always pour solvent on the cloth to avoid contaminating the solvent supply. Wash one small area at a time.

It is important that the surface is dried with a second clean cloth prior to the solvent evaporating to prevent the redeposition of contaminants on the substrate.

Substrate composition can vary greatly. This can affect compound adhesion. It is recommended that adhesion characteristics to a specific substrate be determined prior to application on production parts or assemblies.

PR-2050 Class B Rapid Curing Aerodynamic Smoothing Compound

For a more thorough discussion of proper surface preparation, please consult the SAE Aerospace Information Report AIR 4069. This document is available through SAE, 400 Commonwealth Avenue, Warrendale, PA 15096-0001.

Packing Options

PR-2050 Class B is supplied in a Sempak™ package or a Semco® cartridge. See the container for specific mixing instructions.

Mixing Options

PR-2050 Class B is provided in convenient mix on demand (side-by-side) packaging. Air driven dispensing equipment is recommended for ease of application.

Storage Life

The storage life of PR-2050 Class B is at least 6 months when stored at temperatures between 60°F (16°C) and 80°F (27°C) in original, unopened containers.

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Material Safety Data Sheet (MSDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An MSDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

For emergency medical information call
1-800-228-5635.

Additional information can be found at:
www.ppgaerospace.com

For sales and ordering information call
1-800-AEROMIX (237-6649).

Permapol, Semco and Sempak are trademarks of PRC-DeSoto International, Inc., registered with the U.S. Patent Office.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

Printed in U.S.A.

PRC-DeSoto International, Inc.
12780 San Fernando Road
Sylmar, CA 91342
Telephone (818) 362-6711
Toll Free (800) AEROMIX
www.ppgaerospace.com

Issue Date: 03/10
Supersedes: 09/09
Lit: 2042