



Product Data

Castrol® Aero 40

Landing Gear Shock Strut Fluid

Distributed by QC Lubricants

CAGE CODE 9Y364

7360 Milnor St • Philadelphia, PA 19136

(215) 333-4187 Direct Line

Toll Free **With Extension:** (800) 887-2436

For Technical Assistance **Dial Extension 203** for Stan Jakubowski

For Sales Assistance **Dial Extension 211** for Lu Ann Quinn

QCLubricants.com for Castrol Aero 40 Purchase and Information

Description

Castrol Aero™ 40 is a high quality, mineral based MIL-H-5606 hydraulic fluid containing a highly shear stable viscosity index improver, an anti-oxidant, anti-wear agents, and an approved EP additive which reduce martensitic streaking of landing gear outer cylinders and galling of shock strut upper bearings. Aero 40 is available in either dyed red (Douglas Aircraft) or undyed, straw colored (Boeing Spec BMS 3-32, Type II).

Uses

Aero 40 is designed for use in landing gear shock struts. It is compatible with approved MIL-PRF-6083 and other MIL-H- 5606 qualified hydraulic fluids. It is not completely compatible with synthetic gas turbine lubricants nor with phosphate-ester hydraulic fluids. It is compatible with other petroleum-based and synthesized hydrocarbon lubricants but contamination should be avoided in order to maintain the unique properties of Aero 40. This product is compatible with seals, hoses and paints normally used in shock struts and dispensing equipment connected with this application. While certain grades of the above materials are fully compatible with Aero 40, it is advisable to confirm acceptability of use with either the material manufacturer or Castrol.

Specification

Aero 40 -Red is formulated in accordance with Douglas Aircraft Specification DPS 3.334, referenced as douglas stock number DPM 6176. Additionally, Aero 40 is formulated as an alternative to Boeing Service Letters 707-SL-12-2; 727-SL-12-2; 737-SL-12-2; and 757-SL-27-15-B, which instruct the addition of an EP additive to either the standard or corrosion inhibited mineral based hydraulic fluid for use in their landing gear shock struts.

Typical Characteristics

Method	Test (ASTM)	Result
API Gravity @ 15.6/15.6°C (60/60°F)	D 287	29.2
Pounds per Gallon @ 16°C (60°F)		7.332
Kinematic Viscosity, cSt	D 445	
@ 100°C (212°F)		4.71
@ 40°C (104°F)		13
@ -40°C (-40°F)		510
@ -54°C (-65°F)		2670
Viscosity Index	D 2270	344
Flash Point, COC, °C (°F)	D 92	108 (225)
Fire Point, COC, °C (°F)		116 (240)
Pour Point, °C (°F)	D 97	-57 (-70)
Copper Strip Corrosion, 72 hrs @ 121°C (250°F)	D 130	1a
Four-Ball Wear-Test, AWSD, mm 1 hr @ 1200 rpm, 40 hgf 75°C (167°F)	D 4172	0.43
Falex Wear Characteristics, 500 lbf, Reference Load	D 3233	Pass

Subject to usual manufacturing tolerances.

Castrol, Aero, and the Castrol logo are trademarks of Castrol Limited, used under licence

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet.

It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Limited, Pipers Way, Swindon, Wiltshire SN3 1RE, UK

www.castrol.com/industrial

www.castrol.com/industrial

Castrol Aero 40 Red

15 June 2010, Version 1