# **TECHNICAL DATA SHEET**



# Primer No. 6 Primer

**Description** 

This is a specially formulated silicone based primer for use with a wide range of CHT 1K Condensation / Moisture curing RTV silicone sealants. This primer imparts good adhesion to most metals. It is recommended as a primer for use on non-porous surfaces. For all new applications, it is recommended that customers carry out small-scale tests to determine the suitability of the primer and the strength of bond produced.

## **Key Features**

- Aerospace approved
- Suitable for use with CHT adhesives
- Suitable for non porous surfaces
- For use with most metals

# **Key Applications**

• Rolls Royce MSRR1064

#### Application

Primer for condensation cure 1 part adhesives on metal substrates. Not suitable for polycarbonate and acrylic

#### **Use and Cure Information**

This primer contains solvents which are classified as hazardous under current regulations. Users should read the Safety Data Sheets for this product carefully before use. Surfaces to be bonded should be dry and free from

Property Test Value Method

### **Uncured Product**

23 +/- 2°C and 50 +/-5% humidity

Colour Pale Yellow
Density BS ISO 2781 0.83 g/cm3

Drying / Fixing Conditions 23+/-2°C and 50+/-5%

5 °C / 41 °F

humidity

Flash Point °C

Odour

Rheology

Tack Free Time / Skin

BS 200034

Alcohol
Liquid

15 min

Formation at 23°C/73°F

Viscosity Mixed mPas Brookfield 1 mPas

## Storage

Max Storage Z5 °C / 77 °F Temperature

Min Storage Temperature 5
Shelf Life (mths) 12

grease, oil, dust and release agents. Non-porous substrates, should be solvent degreased prior to application. The primer should be applied with a lint-free cloth or paintbrush and allowed to dry thoroughly at room temperature for a minimum time equal to the tack free time given in this document, before applying the sealant. Drying should be carried out in a well-ventilated area. Do not leave longer than 2 hours. The drying/curing time is dependent on the ambient temperature and humidity. Heat should not be applied to accelerate the drying cycle. Over-application of the primer will result in poor adhesion. As a guide, one litre of Primer should be sufficient for approximately 15 m². It is absolutely important to check the compatibility in preliminary tests if unknown substrates are used.

# Health & Safety

## Safety

Please observe the safety data sheets and the safety statements on the container labels when handling our products. The dangerous goods regulations and the accident prevention regulations of the professional associations must be particularly observed. Keep the safety data sheet of the applied product at hand since it provides useful instructions for the safe use and disposal of the product as well as for actions to be taken in case of accidents.

Revision Date 29 Apr 2021

Revision No

Download Date 28 Jun 2021

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet.

CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time.

The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.