## Cor-Ban®

## CORROSION INHIBITING COMPOUNDS

## D-5035NS



### Product description: HIGH TEMPERATURE CORROSION PREVENTIVE

### FEATURES:

- A heat resistant corrosion preventive
- Provides a firm and waxy coating

### **KEY BENEFITS:**

- D-5035NS is formulated to provide long term protection against corrosion
- The D-5035NS coating can withstand continuous temperatures up to 350°F (177°C), with a short term exposure up to 430°F (221°C)
- The D-5035NS coating contains excellent moisture displacing qualities and adhesion capabilities

### SPECS:

- Boeing QPL for DPM 5217
- NSN: 8030-01-686-7249 (16 fl oz (473 ml) Aerosol)



- The D-5035NS coating provides over 1300 hours of protection on steel in a salt fog environment
- The D-5035NS coating provides superior dampening to metal
- The D-5035NS coating contains acid neutralization properties

Rev: 20067G 11-30-2021





# **Cor-Ban**®

### **CORROSION INHIBITING COMPOUNDS**

## D-5035NS



### Product description: HIGH TEMPERATURE CORROSION PREVENTIVE

### **APPLICATIONS:**

- ✓ A dry film thickness of 1.0 mil (25 microns) provides a transparent coating
- ✓ The D-5035NS aerosol can be used in conjunction with the Formit<sup>®</sup> extensions to provide targeted spray to areas that may be difficult to reach but need to be coated. Please refer to the Formit<sup>®</sup> technical data sheet for more information.
- ✓ Bulk application available as ZC-035
- ✓ Firm and waxy coating of D-5035NS can be easily removed with petroleum solvents

#### **PHYSICAL PROPERTIES:**

- **Evaporation Rate:** Faster Than Ether
- Fungal Growth per Fed-STD-810 Method 508.7: 0 (No Microbial Growth)
- Material V.O.C.: 583 g/L (4.8 lbs/gal)
- Melt Point: 550°F (28°C)
- **Specific Gravity:** 0.8
- Vapor Density: Heavier Than Air

#### AVAILABLE PACK SIZES:

- Case of 12 of 16 fl oz (473 ml) Aerosols-002052
- Special Packaging Upon Request



